

TimberFiber
1656 S. Jackson St.
Jacksonville, TX 75766
hello@timberfiber.com

Complete elemental analysis (dry basis)	
Ash (%)	0.16
Organic Matter (%)	99.84
Total nitrogen (%)	0.18
Phosphorus (%)	< 0.01
Potassium (%)	0.02
Calcium (%)	0.09
Magnesium (%)	0.02
Boron (ppm)	3.9
Copper (ppm)	11.3
Iron (ppm)	29.1
Manganese (ppm)	51.4
Molybdenum (ppm)	< 0.5
Zinc (ppm)	2.1
Aluminum (ppm)	16.0
Sodium (ppm)	101.1
7 days incubated pH	
pH 7 days	5.23
SME	
pH	5.20
Soluble Salts (mmhos/cm)	0.06
Nitrate Nitrogen (N-NO3) (ppm)	< 0.3
Ammonium Nitrogen (N-NH4) (ppm)	0.5
Phosphorus (ppm)	0.9
Potassium (ppm)	17.4
Calcium (ppm)	0.9
Magnesium (ppm)	0.6
Sulfate (ppm)	2.7
Boron (ppm)	0.09
Copper (ppm)	0.04
Iron (ppm)	0.08
Manganese (ppm)	0.07
Molybdenum (ppm)	< 0.02
Zinc (ppm)	< 0.03
Aluminum (ppm)	0.14
Sodium (ppm)	3.6
SAR	0.70